

WA WELLINGTON
ARCHITECTURAL

COORAN PANEL



COORAN PANEL

Wellington Architectural's Cooran Panel is a decorative timber lining board. Named after the Aboriginal word meaning tall trees, this panel was first used on a new aboriginal community health facility. The repetition of the design and natural timber finish will create a feature of any wall.

Panel Features:

- PEFC and FSC Certified timber
- Easy to install
- Custom lengths (to reduce waste)
- Internal or external use (depending on timber species and finish)

The Cooran Panel features a hidden tongue and groove system which provide a seamless finish with fast installation and reduced waste.





Product Details

Panel Size: 70x26mm

Available in our full range of timber species

- Radiata Pine
- Western Red Cedar
- Hoop Pine
- Hemlock
- Victorian Ash
- Spotted Gum
- Blackbutt
- American Oak
- Tasmanian Oak



Please contact us if you have any questions or would like a quote for your next project.









P: 02 6280 8496

E: info@wellingtonarchitectural.com


www.wellingtonarchitectural.com

TIMBER SPECIES GUIDE

Wellington Architectural timber species guide is aimed to assist architects, builders and contractors to determine the right timber to suit your project.

		Seasoned Density	Shrinkage	Hardwood or Softwood	Durability Above Ground	Application
	 <p>Radiata Pine <i>Pinus radiata</i> White to Pale Yellow</p>	550kg/m ³	Medium	Softwood	Low (0-7 years)	Interior Exterior (if treated)
	 <p>Western Red Cedar <i>Thuja plicata</i> Pale Brown to Pink Brown Late wood darker</p>	350kg/m ³	Very Low	Softwood	Reasonably High (15-40 years)	Interior Exterior
	 <p>Hoop Pine <i>Araucaria cunninghamii</i> Pale cream to light yellow</p>	550kg/m ³	Low	Softwood	Low (0-7 years)	Interior Exterior (if treated)
	 <p>Hemlock <i>Tsuga heterophylla</i> Pale cream</p>	500kg/m ³	Medium	Softwood	Low (0-7 years)	Interior
	 <p>Victorian Ash <i>Eucalyptus regnans</i> Pale pink to yellowish brown</p>	660kg/m ³	Very High	Hardwood	Moderate (7-15 years)	Interior
	 <p>Spotted Gum <i>Corymbia maculata</i> Light brown to deep red-brown hues</p>	1100kg/m ³	Medium	Hardwood	High (+40 years)	Interior Exterior
	 <p>Blackbutt <i>Eucalyptus pilularis</i> Golden yellow to pale brown occasional pink hues</p>	900kg/m ³	High	Hardwood	High (+40 years)	Interior Exterior
	 <p>American Oak <i>Quercus alba</i> Light to dark brown</p>	750kg/m ³	Very High	Hardwood	Moderate (7-15 years)	Interior

*All timber species above have a Fire Properties Group Number of 3 (slightly combustible)



Cooran Panel in Spotted Gum
Winnunga Health Facility, Canberra